

General Purpose Plaster for Wall, Column & Beam Plastering Smoothing Layer.**New Formulation with Polymer Latex Powder & Excellent Workability**

Cem Plaster GP 101 # for Grey Base Coat
Cem Plaster GP 202 # for Grey Finish Coat

Description

Cem Plaster GP 202, is a partially non-shrink & non sagging, premixed Polymer Latex Powder & plus Grey Cement for Brick Wall, RC Column & RC Beam plastering works, it's provides extended working life & high early strengths.

Due to its new formulation, **Cem Plaster GP** product is based on selected high grade of Original Portland Grey Cement Type & Rheological Additives. For better workability of smoother & stabilized air voids.

General

The internal & external wall to receive Cem Plaster GP 101 or GP 202 must be constructed from high quality dense common clay brick (min. compressive strength 21 N/mm²), dense aggregate concrete block (min. compressive strength 7 N/mm²) or correctly prepared insitu concrete. Sandlime, flintlime, or calcium silicate bricks, lightweight aggregate blockwork, concrete brickwork, or hollow clay pots should be avoided wherever possible. If these or other forms of construction have been used, take advice from our specified worldwide applicator or the call us directly.

Method of Application**Surface Preparation**

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated but with no surface water. This condition is referred to as saturated surface dry and care should be taken to remove any cement slurry or dust produced during surface preparation. The use of a "fan" shaped water jet is ideal. Steel reinforcements should have all traces of rust removed and be primed.

Application

The minimum thickness of **Cem Plaster GP 101**, Base Layers is 3-12mm. Greater thickness may be applied dependent on site requirements.

The minimum thickness of **Cem Plaster GP 202**, Finishing Layers is 2-3mm. It is not usual to require a thickness greater than this if the Base Coats is applied as specified below.

Base Screed

Cem Plaster GP 101 Base Layers is applied to the correctly prepared surface from a hawk or bucket using a trowel. The minimum thickness of 2-12mm is normally attained in 2/3 trowel applications. This minimum thickness can be achieved either by working from fixed timber grounds, by forming grounds using Base Screed or by the plumb and dot system.

Finishing Coat

The **Cem Plaster GP 202** Finishing Layers must be applied onto set dry **Cem Plaster** Base Layers. The use of "plaster planes" to remove surface irregularities in the Base Screed is not normally recommended as this may produce a friable surface which results in adhesion failure of the **Cem Plaster GP 202** Finishing Coat.

Coverage of Walls	Cem Plaster GP 202 (Finish)	Cem Plaster GP 101 (Base)
Cement Brick Wall	3mm thick @ 4.33/m ² /bag	12mm thick @ 1.76/m ² /bag
Smooth Hollow Block Wall	2mm thick @ 6.57/m ² /bag	6mm thick @ 3.50/m ² /bag
Concrete Column & Beam	2mm thick @ 6.57/m ² /bag	6mm thick @ 3.50/m ² /bag

Technical Data

Cem Plaster GP 101 Cem Plaster GP 202

Ball Pressure Hardness (Brinell)	at 25°C	after 1 days:	12 N/mm ²
		after 3 days	23 N/mm ²
		after 7 days	36 N/mm ²
Density Fresh Mortar		approximately	1.90kg/litre
Initial Set (Vicat)	DIN 52450	at 25°C	approximately ½ hour
Final Set (Vicat)	DIN 52450	at 25°C	approximately >3 hour
Compressive Strength	DIN 52450	at 25°C	after 28 days: 11 N/mm ²
Tensile Strength	DIN 52450	at 25°C	after 28 days: 2.92 N/mm ²
Flexural Strength	DIN 52450	at 25°C	after 28 days: 7.8 N/mm ²

Cleaning of Equipment All tools and mixing containers should be washed and cleaned in water immediately after use before the material sets.

Packaging

Cem Plaster GP 101	40 kg bag
Cem Plaster GP 202	25 kg bag

Storage Shelf Life **Cem Plaster GP 202 or GP 101**, 12 months if stored in dry conditions.

Handling Precaution

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets and the brochure "Hygienic Precautions for Handling Plastic Products"

The General Term & Conditions

All recommendations for use of our product, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for this intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.



LaMaCo System Sdn Bhd

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,
05150 Alor Setar, Kedah, Malaysia

Tel : +60-4-771 1111

Fax : +60-4-772 4444

Http : www.lamaco.com

Email : info@lamaco.com

IMPORTANT: While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.