

White Portland Cement			
Standard		Type	
EN 197		CEM I 52.5N	
AS 3972		GP & HE	
MS888:1991		WHITE PORTLAND CEMENT	
Chemical & Physical Properties		Typical Results	
Loss on ignition	%	2.7	
SO <sub>3</sub> Content	%	3.4	
Whiteness		92.0	
Hunter L		92.6	
Fineness (Blaine)	m /kg	400	
Density	g/cm	3.1	
Initial Setting Time	minutes	130	
Final Setting Time	minutes	160	
Compressive Strength		EN196-1	MS522:Pt2:2005 (Clause 9)
1 day	MPa	20	23
2 days	MPa	33	-
3 days	MPa	-	39
7 days	MPa	50	47
28 days	MPa	66	60

**Important 1:** While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.

**Important 2:** **LAMACO Malaysia** products are not guaranteed against defective materials and manufacture & are sold subject to its standard Terms & Conditions of sale, copies of which may be obtained on request. Whilst **LAMACO Malaysia** endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, it cannot- because it has no direct or continuous control over where or how its products are applied – accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance any advice, specification, recommendation or information given by it.

**Health & Safety** Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheets, available from **LAMACO Malaysia** on request and sent with each delivery.



# Cem WPC 89

White Portland Cement Data Sheet



## LAMACO SYSTEM SDN BHD

Co. No. 1033557-M

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,  
05150 Alor Setar, Kedah. Malaysia

Tel : +60-4-734 5555 Fax : +60-4-772 4444

Http : [www.lamaco.com](http://www.lamaco.com) Email : [info@lamaco.com](mailto:info@lamaco.com)



: +60 19 4486611 +60 19 4786611