

**Self Leveling Polymer & Cement Based, <30mm thick Smoothing Compound****New Formula Two Component System****Description**

**Cem Bond SL 30**, is a partially self-smoothing latex screed with excellent properties of adhesion, flexibility and water resistance. Due to its special formulation, **Cem Bond SL 30** can be used under a damp proof membrane. It is exceptionally easy to mix and produces very low drag on the trowel. In addition to these advantages, **Cem Bond SL 30** can be laid from a feather edge up to at least 12mm in a single application.

**Use**

To level uneven internal sub-floors to provide a smooth surface prior to the application of floor coverings. **Cem Bond SL 30** can be applied on all common sub-floors as concrete and cement/sand screeds, flooring grade asphalt, wood (see preparation below), quarry tiles, internal steel decks, etc.

**Preparation**

The surface of the sub-floor must be clean, sound and free from dust, plaster droppings, grease, paint, polish, and any water-soften able or loosely adhered materials. On absorbent surfaces it may be necessary to damp down, or prime the surface using the **Cem Bond Primer Coats** and allow drying before applying the **Cem Bond SL 30** mortar. Where rising damp is present it is recommended that a suitable surface damp-proof membrane is applied on top of the hardened **Cem Bond SL 30**. The adhesion and hardening of **Cem Bond SL 30** unaffected by the presence of dampness in the sub-floor providing the floor is free of surface water. If sub-floors are impervious, e.g. flooring grade asphalt, or have adhesive residues that will be affected by subsequently applied adhesives, an overall application of **Cem Bond SL 30** at least 3mm thick will be required. This is to ensure uniform drying of the new adhesive or to prevent interaction either with the old adhesive residues or with the asphalt sub-floor. Prior to leveling wooden floors, re-nail and firmly fix all loose boards. Where timber floors are sufficiently rigid but are uneven or worn, or where there is differential movement between floor boards, the technique is to pre-level the timber with **Cem Bond SL 30** prior to screw or ring nail fixing 6mm to 12mm thick plywood sheet to provide a sound and stable base for the new flooring. In all cases sub-floor ventilation must be adequate to prevent deterioration and moisture movement.

**Application**

The mixed material is poured onto the prepared floor surface and spread with a trowel to the required thickness in one operation. Apply at temperatures above 5°C. **Cem Bond SL 30** is partially self-smoothing, but should any trowel marks persist, the surface may be easily smoothed with a wet trowel once the material is "finger-tight", i.e. not fully hardened. This can usually be done after approximately 40 minutes at normal temperatures. Alternatively the trowel marks may be "stoned" down with a carborundum block once the material has hardened.

**Technical Data**

---

Density Fresh Mortar			<b>approximately 1.90kg/litre</b>
----------------------	--	--	-----------------------------------

---

Initial Set (Vicat)	DIN 52450	at 25°C	<b>approximately ½ hour</b>
---------------------	-----------	---------	-----------------------------

---

Final Set (Vicat)	DIN 52450	at 25°C	<b>approximately &gt;3 hour</b>
-------------------	-----------	---------	---------------------------------

---

Compressive Strength	DIN 52450	at 25°C	<b>after 28 days: 50 N/mm<sup>2</sup></b>
Tensile Strength	DIN 52450	at 25°C	<b>after 28 days: 2 N/mm<sup>2</sup></b>
Flexural Strength	DIN 52450	at 25°C	<b>after 28 days: 20 N/mm<sup>2</sup></b>
Ball pressure hardness (Brinell)		at 25°C	<b>after 1 days: 28 N/mm<sup>2</sup> after 3 days 45 N/mm<sup>2</sup> after 7 days 62 N/mm<sup>2</sup></b>

**Mixing:** Mix one 25kg bag of Part B: Modified Powder Cement into 6.kg of Part A: Liquid Polymer. The latex should be shaken and poured into a clean mixing container. The powder is then added gradually with continuous stirring. The use of an **Cem Bond SL 30** mixing paddle with a 10mm chuck electric drill makes this light work. For smaller quantities, 3 volumes of powder should be stirred into one volume of latex.

**Thickness** The standard mix is suitable for applications from a feather edge up to 12mm, however for thicknesses above 8mm the incorporation of up to an equal volume of 3mm single sized aggregate will prove economic. For thicknesses exceeding 12mm and up to 30mm an equal volume of a suitable size of graded aggregate should be incorporated in the standard mix. Mixes with a high aggregate content may require a subsequent smoothing application of the standard mix of **Cem Bond SL 30** and, if this is carried out when the aggregate filled mix has dried priming will help prevent air bubbles, suction and also prolong the flow life. Note that flooring grade asphalt should not be covered with more than 6mm of underlayment.

**Cleaning of Equipment** All tools and mixing containers should be washed and cleaned in water immediately after use before the material sets.

**Drying and Hardening** At normal temperatures:-working time approximately 30 minutes. Workability approximately 2 hours depending on thickness and site conditions. A 3mm thick **Cem Bond SL 30** screed is suitable to receive most floor coverings after 4 hours. The setting and drying characteristics have been selected to suit most conditions and types of surfaces to be screed, enabling **Cem Bond SL 30** to be used for almost every conceivable application. The setting, hardening and drying times will be extended at low temperatures. Thicker applications will require a longer time to dry.

**Coverage** Approximately 1.9kg mortar/m<sup>2</sup>/mm, e.g. one unit will cover approximately 5.70-6.30/m<sup>2</sup> at 3mm thickness.

**Packaging** Net weight 30.88 kg set  
(6 kg/Part A: Liquid & 25 kg/Part B: Powder)

**Storage Shelf Life** **Cem Bond SL 30** Part B Cement, 6 months if stored in dry conditions.  
**Cem Bond SL 30** Part A Polymer, 12 months if stored in dry conditions.

**Handling Precautions**

Wash off any mortar or latex on the skin before it dries. During mixing and application ensure adequate ventilation since the latex component contains ammonia which is volatile and may cause eye watering in confined spaces. Avoid generation of airborne dust during mixing. Cem Bond SL 30 powder contains more than 20% Portland cement and, therefore, in line with current legislation, is classified as irritating to eyes and skin. For this reason the following precautions should be observed:-  
Avoid contact with the skin and eyes; in case of contact with the eyes, rinse immediately with plenty of water and seek medical advice; wear suitable gloves and keep the product out of the reach of children.

**The General Term & Conditions**

All recommendations for use of our product, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for this intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefore. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

The above mentioned details Specified key data are individually checked throughout, guarantee, and included in the certificates of Analysis (CoAs). & Typical key data are spot checked, the value are typical for the product and are indicated for information only. The values are not guaranteed or included in the CoAs.

**LaMaCo System Sdn Bhd**

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,  
05150 Alor Setar, Kedah. Malaysia

Tel : +60-4-771 1111 Fax : +60-4-772 4444

Http : [www.lamaco.com](http://www.lamaco.com)

Email : [info@lamaco.com](mailto:info@lamaco.com)