

## Solvent Free Epoxy Resin Floor Coating For General Flooring and Wall. High Performance, Chemical Resistance & Protection against Corrosion

**Thickness Applied:** From 0.25mm to 0.50mm thick

**Product Application:** **Epo Bond FC** is medium-viscosity solvent free epoxy resin contains. Offers high hardness, chemical resistance and protection against corrosion. The coating has applied on floor or wall system for warehouses, car park decks, garages, shopping centers, precision industrials, hospitals, food processing industrials, electronic industrials, kitchen area and chemical plants other etc.

**Advantage & Properties:** The specific advantage offered by solvent free coating. Very good adhesion, the system recommended for concrete can also be applied on other concrete floors or walls, mineral substrates, as stones, bricks, fibre-glass, plaster, metal surface or even tiles and glass.

**Ultraviolet Resistance:** **Not reflection to eye and no yellowing after 100 hours.**

- ❖ Adhesion is always good on mineral substrates surfacing.
- ❖ Very good flow mechanical properties following optimal cure.
- ❖ Good in no dust from substrate coatings easy to clean, improved visibility.
- ❖ Excellent of chemical resistance, Good on hygienic floor and wall surfacing.
- ❖ Adhesion promoting primers between old with new concrete.
- ❖ Non-toxic, the coating have been cured applied on health floor.

**The chemical composition of resin and hardener is such that it is approval for food contact applications in accordance with recommendations made by the Federal German Board of health (Bundesgesundheitsamt)**

### Mechanical Performance of Properties

Compressive Strength	25°C	[N/mm <sup>2</sup> ]	<b>68 (± 3)</b>
Tensile Strength	25°C	[N/mm <sup>2</sup> ]	<b>23 (± 3)</b>
Elongation at Break	25°C	[%]	<b>2.10</b>
Bond Strength	25°C	[N/mm <sup>2</sup> ]	<b>&lt; 3.20</b>
Flexural Strength	25°C	[N/mm <sup>2</sup> ]	<b>35 (± 3)</b>
Traffic Cured	25°C	[hour]	<b>&gt; 24</b>
Bonding cured	25°C	[h]	<b>06</b>
Viscosity	25°C	[mPas]	<b>7500</b>
Abrasion Resistance		[mg]	<b>80</b>
Modulus of Elasticity		[N/mm <sup>2</sup> ]	<b>12000</b>
Service Temperature		[°C]	<b>- 05 °C until Max. 60 °C</b>
Application Temperature		[°C]	<b>Min. 10 °C until Max. 38 °C</b>
Specific Gravity	25°C	[gm/cm <sup>3</sup> ]	<b>1.20 [± 0.05]</b>

# Epo Bond FC

Solvent Free Epoxy Floor/Wall Coating

## New Reinforced Concrete & Steel

### Surface Preparation

Surface to be repaired or sealed must be clean and sound. Concrete must be free of dust, laitence, sealers, grease and other bond inhibiting contaminants.

Steel surface shall be sand-blasted to SS 2 Standard and de-rust to ST 2 Standard 50mm rich primer is recommended for priming.

Concrete must cured at least 28 days and have with minimum Compressive Strength of 20 N/mm<sup>2</sup>. Those cement slurry, plaster droppings, etc. must be remove, the surface of concrete free of oil, grease, and other loose particles and contamination's.

**Epo Bond FC**, it's easy to applied, there for using roller or brush on R. C. Surfacing & Steel Surfacing. Application must be made in three layer coats with, one layer coat pf **Epo Bond Primer (Refer to Coverage Chart)**

## Existing Reinforced Concrete & Steel

### Surface Preparation

Surface to be repaired or sealed must be clean and sound. Concrete must be free of dust, laitence, sealers, grease and other bond inhibiting contaminants.

Steel surface shall be sand-blasted to SS 2 Standard and de-rust to ST 2 Standard 50mm rich primer is recommended for priming.

Concrete Floor Slab must cured at least 28 days and have with minimum Compressive Strength of 5,000 psi. Those cement slurry, plaster droppings, etc. must be remove, the surface of concrete free of oil, grease, and other loose particles and contamination's.

**Epo Bond FC**, it's easy to applied, therefor using roller or brush on R. C. Surfacing. Application must be made in two layer coats with, first layer coat coverage from 3 - 5 sq. meter per kg and second layer coat coverage from 4 - 8 sq. meter per kg.

### Packing & Size:

10 kg per pack

### Coverage:

3 - 5 sq. meter per kg for first coats  
4 - 6 sq. meter per kg for second coats

## Examples: Calculation Format for Floor/Wall Coating

Products	System	Require of Thickness	Require kg/m2	Unit Rate US\$/kg	Unit Price/m2
Concrete Floor with semi smooth					
<b>Epo Cem WFC Primer</b>	Water Base Primer	0.10mm	0.10		
<b>Epo Bond FC</b>	Solvent Free	0.25mm	0.30		
Total Thickness		<b>0.25mm</b>			
Cost of Material & Wages Per M2					

### Mixing:

Supplied as three-component system. Mix materials with low speed drill and paddle for approximately Four minutes. Insure a thorough mix. Never mix more material than can be used in thirty (30) minutes. Do not apply Epoxy when ambient or surface temperatures are below 50 °F

### Available of Color

Grey, Beige, Green, Blue, Cotta Red & Yellow

### Storage

12 months from date of manufacture in original sealed container stored undercover 25 °C, at ambient temperature away from heat, and dry conditions. For clearing equipment, use special solvent liquid.

# Epo Bond FC

Solvent Free Epoxy Floor/Wall Coating

Test result from below types of chemicals, based on 1 layer primer "Epo Bond Primer" with 3 layers coat of "Epo Bond FC".

Temperature at: 25 °C  
 Thickness at: 0.55mm (0.66 kg/m<sup>2</sup>)  
 Recommended: A Excellent, Not Effected, B Excellent, Slightly Effected, C Excellent, Effected

Name of Chemical Resistant Test Chart	01 month	06 months	1 year
Nitric Acid 10%	A	A	A
Ethyl Alcohol	A	B	B
Toluene	C	C	C
Petrol	A	A	B
Caustic Soda 30%	A	A	A
Acetic Acid 5%	A	B	C
Sulphuric Acid 20%	A	A	A
Sewage Sludge	A	A	A
Salt Water	A	A	A
Ammonia Solution 15%	A	A	A
Phosphoric Acid 10%	A	A	A
Bleach 15% Cl <sub>2</sub>	A	A	B
Sea Water 100% (High ph)	A	A	A
Fuel Oil	A	A	A
Oxalic Acid 10%	A	A	A

## Handling Precautions

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets and the brochure "Hygienic Precautions for Handling Plastic Products"

**Important 1:** While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.

**Important 2:** LAMACO Malaysia products are not guaranteed against defective materials and manufacture & are sold subject to its standard Terms & Conditions of sale, copies of which may be obtained on request. Whilst LAMACO Malaysia endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, it cannot- because it has no direct or continuous control over where or how its products are applied - accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance any advice, specification, recommendation or information given by it.

**Health & Safety** Some of the components of this product may be hazardous during mixing and application. Please consult the relevant Health & Safety Data Sheets, available from LAMACO Malaysia on request and sent with each delivery.



## LAMACO SYSTEM SDN BHD

Co. No. 1033557-M  
 407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,  
 05150 Alor Setar, Kedah. Malaysia

Tel : +60-4-734 5555 Fax : +60-4-772 4444

Http : [www.lamaco.com](http://www.lamaco.com) Email : [info@lamaco.com](mailto:info@lamaco.com)



: +60 19 4486611 +60 19 4786611