

Solvent Free Epoxy Resin, Injecting at Reinforced Concrete Crack Lines, Honey Combs and Sealing Voids Gap with Increase of Loading Bearing for Structures

**High Performance Grade
0.01mm, Very Fine Crack Penetration with 90 cps Viscosity**

Product Description: **Epo Inject Kit** is very low-viscosity epoxy resin grout based on bisphenol-A & containing a reactive diluents. It's two component epoxy resin grout system designed specifically for pressure injection. The low-viscosity resin is also excellent for injecting repair of cracks by gravity feeling. When applied with standard injection equipment of with the Packer, it will effectively grout and seal cracks in horizontal, vertical and overhead surfaces.

Application: Combined with aliphatic and/or cycloaliphatic amines for formulation injecting, good penetration properties system.

Properties: Imparts very low viscosity and long pot life, making injecting system easily workable, and good adhesion to concrete and sandblasted steel. The cured films show below:

- ❖ Good resistance to aliphatic and aromatic hydrocarbons
- ❖ Very good flow mechanical properties following optimal cure
- ❖ Good colour and very good penetration into concrete stability
- ❖ Good resistance to aqueous neutral and alkaline solutions
- ❖ Limited resistance to acids

Mechanical Performance of Properties

Compressive Strength	25°C	[N/mm2]	115 (± 3)
Tensile Strength	25°C	[N/mm2]	55 (± 3)
Elongation at Break	25°C	[%]	30%
Bond Strength	25°C	[N/mm2]	< 6.50
Flexural Strength	25°C	[N/mm2]	48 (± 3)
Traffic Cured	25°C	[hour]	3
Bonding cured	25°C	[hour]	1
Viscosity	25°C	[mPas]	90
Abrasion Resistance		[mg]	225
Modulus of Elasticity		[N/mm2]	25000
Service Temperature	[°C]		- 05 °C until Max. 60 °C
Application Temperature	[°C]		Min. 10 °C until Max. 38 °C

Mixing Viscosity	Bonding Strength To Concrete/after 7 days at 25° C		
Temperature	68 °F	Dry Concrete	1,200 psi (100% concrete cracks)
Viscosity	75 cps	Wet Concrete	870 psi (100% concrete cracks)

Surface Preparation

1. Surface to be repaired or sealed must be clean and sound. Concrete must be free of dust, laitence, sealers, grease and other bond inhibiting contaminants.
2. Drilling of cracks for injecting packer tool ports must be accomplished with vacuum attached swivel drill chuck (no drilling necessary with BISC System).
3. Entry packer tools insert the ports for injecting should be approved devices spaced at appropriate intervals to accomplish the full penetration of the resin grout.
4. Can be using electrical high pressure air-less pump or hand pump to fixing on injection hose pipe with packer connector by connected to packer tool.

Mixing:

Supplied as two-component system. Mix materials with low speed drill and paddle for approximately Two - Four (2 - 4) minutes. Insure a thorough mix. Never mix more material than can be used in thirty (30) minutes. Do not apply Epoxy Inject Kit when ambient or surface temperatures are below 50 °F

Pacing:

3.60 kg pack

Coverage:

10.2 meter/pack/0.8 mm Crack lines

Physical Properties of Epo Inject Kit

Key data of Resin	Specified key data
Aspect (visual)	Liquid
Colour (Gardner. ISO 4630)	≤ 3
Epoxy Index (ISO 3001)	6.2 – 6.5 [eq/kg]
Epoxy equivalent (ISO 3001)	154 – 161 [g/eq]
Viscosity at 25° C (ISO 9371B)	280 – 360 [mPa s]
Density at 25° C (ISO 1675)	1.10 – 1.15 [g/cm3]
Flash point (ISO 2719)	> 142 [°C]
As-supplied form	Liquid
Odour	Slight
Shelf life (storage between 2 – 40 °C)	Several years
Hazardous decomposition products	Carbon monoxide, carbon dioxide (when disposed of in fire) and other toxic gases & vapours
Disposal	Regular procedures approved by Local authorities

Viscosity Temperature	(ISO 9371B) of Resin Grout as a function of temperature				
	[°C]	10	25	30	40
Viscosity at 25° C	[mPas]	850	250	120	60

Mix Ratio Components	Parts by weight
Epoxy Inject Kit Resin	100
Epoxy Inject Kit Hardener	20
Viscosity at 25° C [mPa s]	90
Gel time [min]	80
(Tecam, 100ml, 20° C, 65% RH)	

Key data of Hardener	Specified key data
Aspect (visual)	Colour liquid
Colour (Gardener, ISO 4630)	≤ 4
Amine value (DIN 16945)	12.40-12.70 [eq/kg]
Refractive Index at 25° C (DIN 51423)	1.4625-1.4645
Viscosity at 25° C (ISO 9371B)	≤ 10 [mPas]
H active equivalent weight	40 [g]
Density at 25° C (ISO 1675)	0.87 [g/cm ³]
Flash point (ISO 2719)	> 108 [°C]
As-supplied form	Liquid
Odour	Ammoniacal
Shelf life (storage between 2 – 40 °C)	Several years Hazardous decomposition products Carbon monoxide, carbon dioxide (when disposed of in fire) and other toxic gases & vapours
Disposal	Regular procedures approved by Local authorities

The General Term & Conditions

All recommendations for use of our product, whether given by us in writing, verbally, or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for this intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility therefor. The Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

The above mentioned details Specified key data are individually checked throughout, guarantee, and included in the certificates of Analysis (CoAs). & Typical key data are spot checked, the value are typical for the product and are indicated for information only. The values are not guaranteed or included in the CoAs.

**LaMaCo System Sdn Bhd**

407, Jalan Perusahaan 6, Taman Bandar Baru Mergong,
05150 Alor Setar, Kedah. Malaysia
Tel : +60-4-771 1111 Fax : +60-4-772 4444
Http : www.lamaco.com
Email : info@lamaco.com

IMPORTANT: While the information and data sheet contained in this promotional literature are presented in good faith and believed to be reliable, they do not constitute a part of our terms and conditions of sales unless specifically incorporated in our Order acknowledgement. Nothing herein shall be deemed to constitute a warranty, express or implied, that said information or data sheet are correct or that the products described are merchantable or fit for a particular purpose, or that said information, data sheet or products can be used without infringing patent of third parties.